


DIAMOND ID : 5566006601

POLISHED PROPERTIES [AS PER GIA]

GIA Report No	*****0101		
Lab	GIA	Cut	
Shape	EM	Polish	EX
Carat	5.05	Symmetry	EX
Color	K	Fluorescence	NON
Clarity	VS1	Shade	
Key To Symbol	Crystal, Pinpoint		
Report Comments			


Measurements		Inclusion Details	
Table %	66.00	Center Natts	CN1
Depth %	64.80	Side Natts	SN0
Length	11.83	Center White	CW1
Width	8.39	Side White	SW0
Depth	5.43	Table Open	N
Ratio	1.41	Crown Open	N
Crown Angle	50.57	Pavillion Open	N
Crown Height	11.36	Eye Clean	Y
Pav Angle	56.32	H&A	
Pav Height	49.69	Brilliancy	EX
Girdle	THK	Type2 Cert	--
Culet	NON	Laser Ins.	GIA *****0101

DIMENSIONS



Profile not to actual proportions

PLOTTING



KEY TO SYMBOLS Crystal, Pinpoint

DIMENSIONS

Heart

No Image Available


Arrow

No Image Available

Ideal Scope



Aset Scope



■ Brightness Light Leakage
 Contrast

■ Brightness ■ Less Bright
■ Contrast Light Leakage

Fluorescence

No Image Available

IDEAL scope and ASET Scope are simple tools used to evaluate the light Performance of a diamond. A diamond that reflects a lot of light back to viewer will be full of brilliance, fire and scintillation.



MINING

Country of Origin : SOUTH AFRICA
Mine of Origin : —
Authentication Packet #: _



MANUFACTURING

Location: SOUTH AFRICA
WEIGHT : 14.86 ct



ASSORTING

Analysis and scanning by the
Rough Assortment Specialist
WEIGHT : 14.86 ct


ROUGH



MAPPING

Shape & Size is mapped with
Advanced Technology by
planning technician

SARINE




LASER SAWING

Splitting by Laser Cutting Technician
WEIGHT AFTER SPLITTING: 6.96 ct



LASER CONNING

Conning by Laser Cutting Technician
WEIGHT AFTER CONNING: 6.18 ct



POLISHING

The rough diamond is faceted by a
Skilled Polishing Artisan
5.05 K VS1 EX EX NON

IMAGE



VIDEO



GRADING

Multiple parameters beyond the 4C's
are accessed to grade the diamond
by an experienced Grading Specialist
5.05 K VS1 EX EX NON



CERTIFYING

Laboratory certification by GIA provides
an impartial judgement of the quality
and characteristics of the diamond.
5.05 K VS1 EX EX NON

