



LABORATORY GROWN DIAMOND IDENTIFICATION REPORT



LG407941422
ANTWERP, February 19, 2020

LABORATORY GROWN
DIAMOND
PEAR BRILLIANT
WEIGHT 0.51 CARAT
COLOR J
CLARITY VS 2
POL-SYM VERY GOOD
PROP EXCELLENT
FLUO NONE

NUMBER LG407941422 ANTWERP, February 19, 2020

DESCRIPTION LABORATORY GROWN DIAMOND

SHAPE AND CUT PEAR BRILLIANT

CARAT WEIGHT 0.51 CARAT

Measurements 7.18 x 4.46 x 2.77 mm

CLARITY GRADE VS 2

COLOR GRADE J

Fluorescence NONE

FINISH

Polish - Symmetry VERY GOOD

Proportions EXCELLENT

Table Size 58.5%

Crown Height 15%

Pavilion Depth 44.5%

Girdle Thickness THIN TO MEDIUM (FACETED)

Culet POINTED

Total Depth 62.1%

COMMENT This Laboratory Grown Diamond was created by Chemical Vapor Deposition (CVD) growth process. Type IIa

LASERSCRIBE LABGROWN IGI LG407941422

IDENTIFICATION FEATURES Cloud, Feather

CLARITY SCALE


FLAWLESS/ INTERNALLY FLAWLESS	VERY VERY SLIGHTLY INCLUDED		VERY SLIGHTLY INCLUDED		SLIGHTLY INCLUDED		INCLUDED		
	VVS ₁	VVS ₂	VS ₁	VS ₂	SI ₁	SI ₂	I ₁	I ₂	I ₃

COLOR SCALE

COLORLESS			NEAR COLORLESS			SLIGHTLY TINTED			VERY LIGHT			LIGHT					FANCY COLOR					
D	E	F	G	H	I	J	K	L	M	N	O	P	Q	R	S	T		U	V	W	X	Y

The laboratory grown diamond described in this report has been graded, tested, analyzed, examined and/or inscribed by International Gemological Institute (IGI). Laboratory grown diamonds are diamond crystals created by scientific means and representing essentially all physical, chemical and optical characteristics of natural diamonds. IGI employs and utilizes those techniques and equipment currently available to IGI including without limitations: DiamondView, DiamondSure, FTIR spectroscopy, UV VIS NIR absorption spectrometer, EDXRF spectroscopy, PL (RAMAN) spectrometers.

7.18 x 4.46 x 2.77 mm



Note: Profile not to actual proportions

0-m Security features included in this document are hologram, watermarked paper and additional features not listed, that, as a composite, exceed industry security standards.



See terms and conditions on reverse

All rights reserved. No part of this report may be reproduced or transmitted in any form or by any means, without permission in writing from International Gemological Institute