



ELECTRONIC COPY

LG652416812
Report verification at igi.org



September 10, 2024

IGI Report Number **LG652416812**

Description **LABORATORY GROWN DIAMOND**

Shape and Cutting Style **ROUND BRILLIANT**

Measurements **6.55 - 6.59 X 4.08 MM**

GRADING RESULTS

Carat Weight **1.08 CARAT**

Color Grade **D**

Clarity Grade **VVS 2**

Cut Grade **IDEAL**

September 10, 2024

IGI Report Number **LG652416812**

Description **LABORATORY GROWN DIAMOND**

Shape and Cutting Style **ROUND BRILLIANT**

Measurements **6.55 - 6.59 X 4.08 MM**

GRADING RESULTS

Carat Weight **1.08 CARAT**

Color Grade **D**

Clarity Grade **VVS 2**

Cut Grade **IDEAL**

ADDITIONAL GRADING INFORMATION

Polish **EXCELLENT**

Symmetry **EXCELLENT**


Fluorescence **NONE**

Inscription(s) **IGI LG652416812**

Comments: As Grown - No indication of post-growth treatment.

This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process. Type II

PROPORTIONS



Sample Image Used


COLOR

D E F G H I J Faint Very Light Light

CLARITY

IF VS¹⁻² VS¹⁻² SI¹⁻² I¹⁻³

Internally Flawless Very Very Slightly Included Very Slightly Included Slightly Included Included



ADDITIONAL GRADING INFORMATION

Polish **EXCELLENT**

Symmetry **EXCELLENT**

Fluorescence **NONE**

Inscription(s) **IGI LG652416812**

Comments: As Grown - No indication of post-growth treatment.

This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process. Type II



IGI



September 10, 2024	1.08 CARAT	D	Pointed
IGI Report No LG652416812	EXCELLENT	VVS 2	EXCELLENT
ROUND BRILLIANT	EXCELLENT	IDEAL	EXCELLENT
6.55 - 6.59 X 4.08 MM	Medium (Faceted)	62.1%	NONE
Carat Weight	1.08 CARAT	66%	IGI LG652416812
Color Grade	D		
Clarity Grade	VVS 2		
Cut Grade	IDEAL		
Depth	62.1%		
Table	15.5%		
Girdle	43%		
Culet	None		
Polish	EXCELLENT		
Symmetry	EXCELLENT		
Fluorescence	NONE		
Inscriptions(s)	IGI LG652416812		
Comments:	As Grown - No indication of post-growth treatment. This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process. Type II		