

GEMOLOGICAL INSTITUTE

### **ELECTRONIC COPY**

### LABORATORY GROWN DIAMOND REPORT

# PROPORTIONS

**CLARITY CHARACTERISTICS** 

**KEY TO SYMBOLS** 

Red symbols indicate internal characteristics.


Green symbols indicate external characteristics.

October 8, 2024		
IGI Report Number	LG657459943	
Description	LABORATORY GROWN DIAMOND	
Shape and Cutting Style	ROUND BRILLIANT	
Measurements	6.56 - 6.60 X 4.08 MM	
GRADING RESULTS		
Carat Weight	1.09 CARAT	
Color Grade	D	
Clarity Grade	VS 1	
Cut Grade	IDEAL	
ADDITIONAL GRADING INFORMATION		

Polish	EXCELLENT
Symmetry	EXCELLENT
Fluorescence	NONE
Inscription(s)	()31 LG657459943

Comments: As Grown - No indication of post-growth treatment.

This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process. Type II



LG657459943

Report verification at igi.org



Sample Image Used

Faint

VS <sup>1-2</sup>

Very

Slightly Included

THIS DOCUMENT WAS PRODUCED WITH THE FOLLOWING SECURITY MEASURES: SPECIAL DOCUMENT PAPER, INK SCREINS, WATERMARK BACKGROUND DESIGNS, HOLOGRAM AND OTHER SECURITY FEATURES NOT LISTED AND DO EXCEED DOCUMENT SECURITY INDUSTRY GUIDELINES.

Light

1.3

Included

Very Light

SI 1 - 2

Slightly

Included

COLOR

CLARITY

Internally

Flawless

IE

DEFGHIJ

VVS <sup>1 - 2</sup>

Very Very

Slightly Included

© IGI 2020, International Gemological Institute

## October 8, 2024

OCIODEI 0, 2024	
IGI Report Number	LG657459943
Description LAB	ORATORY GROWN DIAMOND
Shape and Cutting Style	ROUND BRILLIANT
Measurements	6.56 - 6.60 X 4.08 MM
GRADING RESULTS	
Carat Weight	1.09 CARAT
Color Grade	D
Clarity Grade	VS 1
Cut Grade	IDEAL

LABORATORY GROWN DIAMOND REPORT

56% 34.3° 159 Medium To Slightly 62% Thick 40.8° 43% (Faceted) Pointed

#### ADDITIONAL GRADING INFORMATION

Polish	EXCELLENT
Symmetry	EXCELLENT
Fluorescence	NONE
Inscription(s)	1631 LG657459943
Comments: As Grown - No indication of post-growth treatment. This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process. Type II	



