



INTERNATIONAL
GEMOLOGICAL
INSTITUTE

ELECTRONIC COPY

LABORATORY GROWN DIAMOND REPORT

July 28, 2025

IGI Report Number

LG725518937

Description

LABORATORY GROWN DIAMOND

Shape and Cutting Style

HEART BRILLIANT

Measurements

6.64 X 7.42 X 4.30 MM

GRADING RESULTS

Carat Weight

1.21 CARAT

Color Grade

D

Clarity Grade

VVS 2

ADDITIONAL GRADING INFORMATION

Polish

EXCELLENT

Symmetry

EXCELLENT

Fluorescence


NONE

Inscription(s)

 LG725518937

Comments: As Grown - No indication of post-growth treatment.
This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process.
Type II

PROPORTIONS



Medium To Slightly Thick (Faceted)

56%

15.5%

39.5%

58%

Pointed



Sample Image Used

COLOR

D

E

F

G

H

I

J

Faint

Very Light

Light

CLARITY

IF

VS¹⁻²

VS¹⁻²

SI¹⁻²

I¹⁻³

Internally Flawless

Very Very Slightly Included

Very Slightly Included

Slightly Included

Included



© IGI 2020, International Gemological Institute



FD - 10 20

LABORATORY GROWN DIAMOND REPORT



July 28, 2025

IGI Report Number

LG725518937

Description

LABORATORY GROWN DIAMOND

Shape and Cutting Style

HEART BRILLIANT

Measurements

6.64 X 7.42 X 4.30 MM

GRADING RESULTS

Carat Weight

1.21 CARAT

Color Grade

D

Clarity Grade

VVS 2

ADDITIONAL GRADING INFORMATION

Polish

EXCELLENT

Symmetry

EXCELLENT

Fluorescence

NONE

Inscription(s)

 LG725518937

Comments: As Grown - No indication of post-growth treatment.
This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process.
Type II



IGI

July 28, 2025

IGI Report No LG725518937

HEART BRILLIANT

6.64 X 7.42 X 4.30 MM

Carat Weight

1.21 CARAT

Color Grade

D

Depth

VVS 2

Table

58%

Girdle

55%

Medium to Slightly Thick (Faceted)

Pointed

Polish

EXCELLENT

Symmetry

EXCELLENT

Fluorescence

NONE

Inscription(s)

 LG725518937

Comments: As Grown - No indication of post-growth treatment.
This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process.
Type II